

Specifications for ‘Crystallazzo’ Cement Concrete Terrazzo Tiles of size (Sizes : 250x250x24mm, 300x300x28mm, 400x400x31mm, 500x500x32 mm)

Supply of Customized “Crystallazzo Series” Terrazzo Flooring Tiles with ground finish with

- Special colour coordinated aggregates in face mix.
- Colours specified by the architects, using UV resistant colour pigments from Lanxess.

Sr.	Parameters	Minimum Requirements (Testing as per IS 1237:1980)
1.	Percentage Water Absorption	Not over 7.5%
2.	Wet transverse strength	Not less than 5.5N/mm ²
3.	Average wear in Thickness- Abrasion	Average wear not more than 2mm
4.	Size (length + breadth)	<0.5mm
5.	Thickness of wearing layer	Not less than 8mm
6.	Variation in Thickness of tiles	Variation not to exceed 3mm
7.	Flatness of tile surface	Concavity / convexity not to exceed 0.5mm

- The manufacturing company must be an ISO 9001:2008 certified Company or should have equivalent quality management systems in place to ensure quality product.
- The Terrazzo tiles must confirm to IS 1237:1980.
- The Tiles must be manufactured on automatic machines with mechanical vibration and rubberized moulds.
- The Tiles must be ground on Linear Grinding Machine.
- The Tiles will be made using wear resistant materials in the face mix as specified by the architects.
- The Tiles must be cured in controlled environment to ensure efflorescence free material.
- The manufacturer must have in house testing laboratory to carry out all testing including Compressive strength testing, Water absorption, abrasion resistance etc.