

Specifications for Exposed aggregate Cement Concrete Pebbled Terrazzo Tiles of size (Sizes : 300x300x30mm, 400x400x34mm)

Supply of Customised “**Pebblino**” Series Terrazzo Tiles with special coloured pebble aggregates specified by Architects acrylic sealed finish.

Parameters	Minimum Requirements (Testing as per IS 1237:1980)
1 Percentage Water Absorption	Not over 7.5%
2 Wet transverse strength	Not less than 5.5N/mm ²
3 Average wear in Thickness-Abrasion	Average wear not more than 2mm
4 Size (length + breadth)	<0.5mm
5 Thickness of wearing layer	Not less than 8mm
6 Variation in Thickness of tiles	Variation not to exceed 3mm
7 Flatness of tile surface	Concavity / convexity not to exceed 0.5mm
8 Colours	UV Light resistant fast colours from BAYFERROX only to be used min 3% to be used

- The manufacturing company must be an ISO 9001:2000 certified Company or should have equivalent quality management systems in place to ensure quality product.
- The Terrazzo tiles must confirm to IS 1237:1980.
- The tiles must be manufactured on automatic machines with mechanical vibration and rubberized moulds.
- The Tiles will be made using wear resistant materials in the face mix as specified by the architects.
- The Tiles must be cured in controlled environment to ensure efflorescence free material.
- The manufacturer must have in house testing laboratory to carry out all testing including Compressive strength testing, Water absorption, abrasion resistance etc.